

PRODUCT DATA SHEET Interior Concrete Wall Paneling MasterFormat 09 78 19

DESCRIPTION AND USES

Concreate Wall Panels:

These thin concrete panels posses the attractive mottled look and smooth feel that only real burnished concrete can provide. They are lightweight and durable and can be easily adhered to walls and other vertical interior surfaces.

Concreate Panels may be applied to gypsum board, plaster, concrete, unit masonry, engineered wood panels, and other acceptable substrates.

Concreate Ceiling Tiles:

For overhead use, panels can be installed in most standard ceiling suspension grids; (do not place insulation or other back loads on panels).

Concreate Veneer - Other Uses:

Panels can also be used on cabinets, countertops, or furniture; contact Concreate for additional information.



PHYSICAL ATTRIBUTES

STANDARD CONCRETE COLORS



CW101 Natural Grey Concrete



CW301 Mineral Sand Concrete



CW306 Metallic Copper Concrete



CW107 Titanium Black Concrete



CW309 Moss Green Concrete



CW108 Metal Grey Concrete CW109

Bronze Grev

Concrete

COMPOSITION

Concrete Panel: 4 mm (½-inch) thick proprietary blend of portland cement, select fine aggregate, admixtures, recycled fibers, and fade resistant pigments.

Oil Finish: Our floors are finished with three coats of high solids, natural oils to increase the luster, durability, and stain.

SIZE, AREA, AND MASS

Concrete Panels:

- Size: 1200 x 600 x 4 mm (47-1/4 x 23-5% x 1/8 inch)
- Area: 0.72 m2 (7.75 sq.ft.)
- Mass: 6.5 kg/M2 (1.3 lb/sq.ft.)

concrete innovation

PRODUCT DATA SHEET Interior Concrete Wall Paneling MasterFormat 09 78 19

TESTING DATA

ATTRUBUTE	PROTOCOL	PERFORMANCE	COMMENT
Fire Classification	ASTM E84-14	Class A	
Asbestos Content	NIOSH 9002	Not detected.	
Total Volatile Organic Compound (TVOC)	ISO 16000-6 and ISO 16000-9	1111 · : g/m ³	Meets EU requirements.
Volatile Organic Compound (VOC)	CDPH Method V1.1 (CA Spec, 01350)	Compliant for schools and offices.*	
Formaldehyde	EN 717-1	Not detected	
Lightfastness	ISO 105-B02	Grade 3-4	
Chemical Resistance	EN 423	Class O - No Affect • White vinegar • Isopropyl alcohol • Mineral oil • NaOH (5%) • Bleach (5.25% NaOCI) • Olive Oil • Red & white wine • Coffee & tea	Class 1- Very Slight • Hydrocloric acid (5% HCl) • Sulfuric acid (5% H2SO4

1. See standards for full description of tests and test reports for full discussion of results. 2. Additional testing in progress, contact Concreate for current information.

Wall Panels:

Our products have been independently tested for conformance with environmental requirements for VOC and formaldehyde emissions; asbestos, lead, and cadmium content.

Adhesive:

Concreate Wall Adhesive is a one-component, high-solids, modified-silane polymer with low VOC-content, low odor, and no shrinkage. It has high initial bond strength and is moisture curing, moisture resistant, and permanently elastic. It can also be used as a joint filler between panels and abutting surfaces; it is paintable, sandable, and grey in color.

LIMITED WARRANTY

Concreate provides a 10-year warranty for single-family, owner-occupied homes and condominiums; and a 5-year warranty on other projects. Visit www.Concreate.net for more detailed warranty information.

CONTACT INFORMATION

Concreate Headquarters:

1730 E Holly Ave Ste 728 El Segundo, CA 90245 +1 855.265.2116 www.Concreate.net info@concreate.net

DEALER IMPRINT AND SUBMITTAL STAMPS

© ® 2015, Concreate LLC. Issued 2016-10, subject to change. Disclaimer: This information only a general guide and is not intended to be exhaustive. It is for use by qualified design and construction professionals only. Further information is available upon request.